

# SeaRox® WM 600

SeaRox WM 600 is made of non-combustible stone wool. One side is faced with 1" galvanized wire netting. The wire netting is stitched on with galvanized wire. The product can be supplied with reinforced alu foil.



## Application

SeaRox WM 600 is mainly for thermal and A-30 fire rated applications.

## Product properties


Properties	Performance		Norm
Thermal conductivity	T (°C) λ (W/mK)	10 0,039	EN 12667
Nominal density	45 kg/m <sup>3</sup>		EN 1602 / IMO
Compressive strength	-		EN 826
Fire classification	Non-combustible Approved for A constructions Low flame-Spread Properties		Acc. IMO FTP code
Water absorption (short term)	< 1 kg/m <sup>2</sup>		EN 1609
Max. Application Temperature	Wool: 250°C Facing: 80°C		-
Sound absorption directly mounted			ISO 354 (approximated) Evaluated after ISO 11 654
Facings	Reinforced alu foil		IMO A.653(16) (low flame - spread)

## Dimensions

### SeaRox WM 600:

Thickness (mm): 50 mm Length (mm): 3000 mm Width (mm): 600 mm

Local variations in standard dimensions might occur.



0575

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.